

IN THE CLAIMS

Kindly amend the claims as follows:

Sub  
D1  
C3

1. (Three Times Amended) A heat shrinkable film comprising a homogeneous linear single site catalyzed copolymer of ethylene and an alpha-olefin having from three to ten carbon atoms, said copolymer having a density of at least [about 0.906] 0.901 g/cc, wherein said heat shrinkable film has been extruded and cooled to its solid state by cascading water, and thereafter heated to its softening temperature and stretched in its machine and transverse directions followed by being quenched, so that said heat shrinkable film will return to its unstretched dimensions when heated.

Sub  
D2  
C4

16. (Three Times Amended) A heat shrinkable film having a symmetrical structure comprising:  
outer layers comprising a propylene homopolymer or copolymer; and  
a core layer comprising a homogeneous linear single site catalyzed copolymer of ethylene and an alpha-olefin having from [four] three to eight carbon atoms, said homogeneous copolymer having a density of at least [0.906] 0.901 g/cc;  
wherein said heat shrinkable film has been extruded and cooled to its solid state by cascading water, and thereafter heated to its softening temperature and stretched in its machine and transverse directions followed by being quenched, so that said heat shrinkable film will return to its unstretched dimensions when heated.

Sub  
P3  
C

18. (Three Times Amended) A heat shrinkable multilayer film comprising:

a heat sealing layer;

an inner layer comprising a homogeneous linear single site catalyzed copolymer of ethylene and an alpha-olefin having from three to eight carbon atoms, said copolymer having a density of at least [0.906] 0.901 g/cc; and

a barrier layer; and

wherein said heat shrinkable film has been extruded and cooled to its solid state by cascading water, and thereafter heated to its softening temperature and stretched in its machine and transverse directions followed by being quenched, so that said heat shrinkable film will return to its unstretched dimensions when heated.

Sub  
P4  
C

28. (Three Times Amended) A heat shrinkable multilayer film comprising:

a heat sealing layer comprising a homogeneous linear single site catalyzed copolymer of ethylene and an alpha-olefin having from three to eight carbon atoms, said copolymer having a density of at least [0.906] 0.901 g/cc; and

a barrier layer; and

wherein said heat shrinkable film has been extruded and cooled to its solid state by cascading water, and thereafter heated to its softening temperature and stretched in its machine and transverse directions followed by being quenched, so that said heat shrinkable film will return to its unstretched dimensions when heated.

Sub  
85  
C7

35. (Three Times Amended) A heat shrinkable film comprising at least two layers wherein at least one of said layers comprises a homogeneous linear single site catalyzed copolymer of ethylene and an alpha-olefin having from three to eight carbon atoms, said copolymer having a density of at least [0.906] 0.901 g/cc, and wherein at least one of said layers is crosslinked, and wherein said heat shrinkable film has been extruded and cooled to its solid state by cascading water, and thereafter heated to its softening temperature and stretched in its machine and transverse directions followed by being quenched, so that said heat shrinkable film will return to its unstretched dimensions when heated.

36. (Three Times Amended) A heat shrinkable multilayer film having a symmetrical structure comprising:

outer layers comprising a homogeneous linear single site catalyzed copolymer of ethylene and an alpha-olefin having from three to eight carbon atoms, said copolymer having a density of at least [0.906] 0.901 g/cc; and

an inner core layer; and

wherein said heat shrinkable film has been extruded and cooled to its solid state by cascading water, and thereafter heated to its softening temperature and stretched in its machine and transverse directions followed by being quenched, so that said heat shrinkable film will return to its unstretched dimensions when heated.

52h  
DB  
Cig

42. (Twice Amended) A seamless tubing comprising a multilayer, heat shrinkable film comprising a homogeneous linear single site catalyzed copolymer of ethylene and an alpha-olefin having from three to ten carbon atoms, said copolymer having a density of at least [0.906] 0.901 g/cc, wherein said film has been extruded and cooled to its solid state by cascading water, and thereafter heated to its softening temperature and stretched in its machine and transverse directions followed by being quenched, so that said film will return to its unstretched dimensions when heated.

43. (Twice Amended) A process for making a heat-shrinkable film, comprising:

- (A) extruding a film comprising a homogeneous linear single site catalyzed copolymer of ethylene and an alpha-olefin having from three to ten carbon atoms, said copolymer having a density of at least [0.906] 0.901 g/cc; and
- B) cooling the film to the solid state by cascading water;
- C) reheating the film to a softening temperature of the homogeneous linear single site catalyzed copolymer;
- D) stretching the film so that an oriented molecular configuration is produced;
- E) quenching the film while substantially retaining its stretched dimensions to set the film in the oriented molecular configuration.

Kindly add the following newly-presented claims:

Sub 7  
81  
---57. A heat shrinkable film comprising a homogeneous linear single site catalyzed copolymer of ethylene and an alpha-olefin having from six to ten carbon atoms, said copolymer having a density of at least 0.901 g/cc, wherein said heat shrinkable film has been extruded and cooled to its solid state by cascading water, and thereafter heated to its softening temperature and stretched in its machine and transverse directions followed by being quenched, so that said heat shrinkable film will return to its unstretched dimensions when heated.

19  
81  
58. The heat shrinkable film according to Claim 57, wherein the homogeneous linear single site catalyzed copolymer is a copolymer of ethylene and hexene.

59. The heat shrinkable film according to Claim 57, wherein the homogeneous linear single site catalyzed copolymer is a copolymer of ethylene and octene.

60. The heat shrinkable film according to Claim 57, wherein the film is a multilayer film.

Sub 7  
81  
61. The heat shrinkable film according to Claim 60, wherein the multilayer film has at least 3 layers.

62. The heat shrinkable film according to Claim 61, wherein the homogeneous linear single site catalyzed copolymer is present in an inner layer.